

材料牌号
Material Brand

Winthane™ 65595

材料类别
Material Category

MDI-PCL-HQEE

特性与操作


Features and operations

热风干燥 Air Drying	除湿干燥 Dehumid	露点 Dew Point	体积熔融指数 Melt Index	喷嘴温度 Nozzl TEMP	模具温度 Mould TEMP
--------------------	-----------------	-----------------	----------------------	--------------------	--------------------

110°C/4H 100°C/3H -30°C 12cm³/10min 215°C 30-50°C


机筒一区温度
1 Zone TEMP
机筒二区温度
2 Zone TEMP
机筒二区温度
3 Zone TEMP

215°C
215°C
215°C



物理性能指标

Physical Property



*以上技术参数均为采用DIN标准，在实验室中测试所得，样件测试前在120°C温度下处理24h

The values shown in this information are aquired in laboratory tests according to DIN standard .